

Product data sheet



Product: DP13-CC
DECO PRIME 13 CC - Millfinish
climate ceiling material

4700/1054/001/04.16

Alloy	¹	AlMg 1
Hardness	²	1/2 hard

Supply form

Metal Thickness	[mm]	Coil, strip, sheet, blanks 0,30 - 1,50
Width up to	[mm]	1250,00

Mechanical Properties

Yield strength Rp 0,2	[MPa]	150 - 175
Tensile strength Rm	[MPa]	160 - 185
Elongation at break A50	[%]	2
Bending radius		1,5 x gauge of material

Physical Properties

thermal emissivity (30°C)	[%]	74
---------------------------	-----	----

Tolerances

Metal Thickness	[mm]	0,30 - 0,50 ± 0,04
	[mm]	0,51 - 0,60 ± 0,05
	[mm]	0,61 - 1,00 ± 0,06
	[mm]	1,01 - 1,20 ± 0,07
	[mm]	1,21 - 1,50 ± 0,09
max Width/Coil	[mm]	+ 3,00 / - 0,00
Width Slit Coil	[mm]	± 0,20 standard
Longitudinal Curvature	[mm]	1,00 on a measuring length of 1000 mm
Length	[mm]	0 - 600 + 1,00 / - 0,00
	[mm]	601 - 1500 + 1,50 / - 0,00
	[mm]	1501 - 2500 + 2,50 / - 0,00
	[mm]	2501 - 3500 + 3,50 / - 0,00
Flatness	[%]	1 % of wavelength, max. 8 mm
Transversal Divergency	[mm]	1,5 (D1-D2)
		other tolerances on request

Protective Film

Protective Film Type	[-]	PE - Film
Protective Film Thickness	[µm]	50 - 60

Oxide Layer

Oxide layer front side	[µm]	2,50 ± 0,50
------------------------	------	-------------

¹ based on DIN EN 573-3 (Aluminium) resp. Rolling mill standard

² based on DIN EN 485-2 (Aluminium) resp. Rolling mill standard

