

Product data sheet



Product: DP14
DECO PRIME® ELOX
Longline Brushed 14

4700/1147/001/11.18

Alloy	¹	AlMg 1
Hardness	²	1/2 hard

Treatment front side	(S1)	anodised
Treatment reverse side	(S2)	anodised

Supply form

		Coil, strip, sheet, blanks
Metal Thickness	[mm]	0.80
Width up to	[mm]	1250,00

Mechanical Properties

Yield strength Rp 0,2	[MPa]	120
Tensile strength Rm	[MPa]	140
Elongation at break A50	[%]	2
Bending radius		1,5 x gauge of material

Tolerances

Metal Thickness	[mm]	0.80 ± 0.06
max Width/Coil	[mm]	+ 3,00 / - 0,00
Width Slit Coil	[mm]	± 0,20 standard
Longitudinal Curvature	[mm]	1,00 on a measuring length of 1000 mm
Length	[mm]	0 - 600 + 1,00 / - 0,00
	[mm]	601 - 1500 + 1,50 / - 0,00
	[mm]	1501 - 2500 + 2,50 / - 0,00
	[mm]	2501 - 3500 + 3,50 / - 0,00
Flatness	[%]	1 % of wavelength, max. 8 mm
Transversal Divergency	[mm]	1,5 (D1-D2)
		other tolerances on request

Protective Film

Protective Film Type	[-]	PE - Film
Protective Film Thickness	[µm]	50 - 60

¹ based on DIN EN 573-3 (Aluminium) resp. Rolling mill standard

² based on DIN EN 485-2 (Aluminium) resp. Rolling mill standard

